



sampling products

Phone: 418.227.4279 | 1.800.933.5232 | Fax: 418.227.3188 | info@samplingproduct.com | www.samplingproduct.com

	ORIGINAL	6 GRAM TEST	
DR	32.4	34.6	= 2.20
KIT	32.3	34.1	= 1.80
BR EAST	32.5	34.2	= 1.70
BR WEST	32.5	34.3	= 1.80
GYM NORTH	32.5	34.4	= 1.90
GYM SOUTH	32.4	34.8	= 2.00

$$\text{DR} \quad \frac{2.2 \times 2.057 \times 24 \times 1000}{66 \times 454} = \frac{108609.6}{29964} = 3.62466960$$

$$\text{KIT} \quad \frac{1.8 \times 2.057 \times 24 \times 1000}{66 \times 454} = \frac{88862.4}{29964} = 2.9656$$

$$\text{GYM} \quad \frac{2.00 \times 2.057 \times 24 \times 1000}{66 \times 454} = \frac{98736}{29964} = 3.295154$$

MOISTURE LEVEL OF THE SUB-FLOOR SHOULD NOT EXCEED 3665 / 1000 sq.ft. / 24 hrs.

MOISTURE FORMULA

$$\frac{\text{GAIN IN WEIGHT (GRAMS)} \times 2.057 \times 24 \times 1000}{\text{HRS. EXPOSED} \times 454} =$$